

008_SELFORM©THERMAL TOP BISPHENOLFREE_A

PRODUCT: SELF-ADHESIVE TOP COATED THERMAL PAPER

APPLICATIONS: SELF-ADHESIVE LABELS

Thickness		144 µm	PN-ISO 534	+/-15
	Туре	Top coated thermal paper, bisphenlolfree		
Face stock	Basis Weight	76 g/m2	PN-ISO 536	+/- 5
	Thickness	82 µm	PN-ISO 534	+/- 8
Liner	Туре	Supercalendered glassine paper		
	Basis Weight	58 g/m2	PN-ISO 536	+/- 5
	Thickness	50 μm	PN-ISO 534	+/- 7
Adhesive	Туре	Permanent, acrylic, water borne		
	TACK	10 N	FTM 9, glass	min. 8 N
Minimum application temperature		5 °C		
Service temperature		-10 °C ÷ 80 °C		
Roll width		+/- 1 mm		
Roll lenght		min 1850 lm max 2050 lm		
Number of joints		max 2 / 2000 lm		
Storage conditions		Stored at constant temperature (18-25 °C) and 40-60% RH. Warehouse should be clean and dry. Materials, if not used, should stay in their original packaging, to be well protected against dust and dirt. Do not expose to direct sunlight and other heat sources.		
Shelf life		24 months, only in reference to materials produced by Papiery Powlekane Pasaco Sp. z o.o., not to materials further processed.		
Printing method		Product can be converted by all conventional conversion methods. Exporsure above 50°C may cause premature imaging. Alcohol based inks may cause discoloration of the thermosensitive coverage. Water based inks and varnishes are recommened. Before conversion ink test is advisable.		
Food contact		Used materials comply with the food directives and legislations.		

PRODUCT DATA SHEET



	Paper has tendency to discolour and turn yellowish, but it does		
Additional information	not affect the scannability of the printed intormation. Limited		
Additional information	resistance to thermal image scratching or smudging. Limited		
	resistance to the heat, moisture, light, fat and water.		
	Not recommended to be used for labeling surface firmly curved.		
	If necessary on the surfaces of application difficult and rough,		
Attention	such as transport labels (containers, cartons) luggage tags, mail		
	applications, courier services, etc. it is recommended to perform		
	the tack test on a given surface.		

The technical data sheet has been prepared in good faith. The purchaser should independently test the suitability of the product for a particular application.

Valid from : 2023-04-06

008_SELFORM_THERMAL TOP Bisphenolfree-38_GL-10-16-18_A_EN